



## LDPE NATURAL

### Applications:

Blown film extrusion, pipe extrusion.

Properties	Typical Value	Method
Density	0.92- 0.94 g/cm	ISO 1183
Melt Index 190°C/2.16 kg)	0.9 to 1.2 g/10 min	ISO 1133
Tensile Strenght at Break (50 mm/min)	≥ 18 Mpa	DIN 53504
Elongation at Break (50 mm/min)	≥ 600 %	DIN 53504
Ash Content	≤ 1 %	DIN 3451
Form	3-5 mm granules	
Filter Size	110 Mesh	

### Storage:

This product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight, sparks, heat and flame. Inappropriate storage conditions can lead to colour changes and the deterioration in physical properties. It is advised to process pellets within 6 months after delivery.

### Packaging:

Our products are packed in 1250 Kg Big Bags.

### Notes:

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests. Please contact us for product samples.

**RePlast Geri Dönüşüm ve Teknolojileri San ve Tic A.Ş**

Sancaktepe Mah. Gürpınar Cad. No 9/1-2 Silivri, İstanbul, Türkiye

T: +90 212 721 7277 / F: +90 212 721 7276 / [info@replastind.com](mailto:info@replastind.com) / [www.replastind.com](http://www.replastind.com)